

# SUPREME SEAL VT

## Low VOC Pure Acrylic Concrete Sealer

### DESCRIPTION

SUPREME SEALVT is a tough pure acrylic concrete sealer in a solvent base. It is designed to protect and beautify all types of concrete with a high gloss durable clear coating. SUPREME SEAL 25 VT is non-yellowing to preserve the appearance of all types of decorative concrete. SUPREME SEALVT is formulated as follows:

**SUPREME SEAL 25 VT** is a High solids (25%), slow drying formulation for high gloss in fewer coats and extended workability also available in Matte.

**SUPREME SEAL 19 VT** Lower solids, slow drying formulation for easy sprayability and resealing existing surfaces with Supreme Seal.

### FEATURES

★High Gloss

★Durable

★High Solids

★U.V. Resistant

### PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Be sure to remove any foreign coating unless previous coating is same or similar solvent-based sealer. Make sure the surface is clean, dry and sound. Clean oily concrete with Clemons' CLEANER DEGREASER. Use a bristle brush for heavily oiled spots. If surface is slick, etch with Clemons' ETCH & CLEAN. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles to form. For pavers, sweep away any loose sand.

### APPLICATION

Brush may be used where roller won't reach. Do not pour directly from can to concrete. Apply evenly from can or other metal container with appropriate roller. Use a long nap roller for exposed aggregate, a medium nap roller for textured surfaces and a short nap roller for smooth surfaces. Keep roller soaked by dipping on every stroke. Every few feet turn perpendicular to the first coat, and cross roll without re-dipping. Wait until the surface is tack-free before applying a second coat. The continual dipping with the first coat gives a heavy application and the cross-rolling allows for an even application. If spraying, use a metal container and clean up immediately with aromatic solvent such as A-100, Xylene, toluene, or lacquer thinner containing the previously mentioned solvents. Do not thin product. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48-72 hours. Cooler temperatures or increased humidity will slow the dry.

### NET COVERAGE RATE

Two thin coats are recommended.

Smooth Troweled: 300 ft<sup>2</sup> per gallon

Broom Swept: 200 ft<sup>2</sup> per gallon

Textured or Stamped: 200 ft<sup>2</sup> per gallon

Exposed Aggregate and Pavers: 100 ft<sup>2</sup> per gallon

### TECHNICAL DATA

VOC: standard <400 g/L

Flash Point: 40° F

DOT: UN1263,Paint,3, PG II

### HMIS

Health 2 Flammability 3

Reactivity 0 Protection B

### SLIP RESISTANCE

For additional slip resistance, apply one coat of SUPREME SEAL. Mix SUPER GRIP into sealer and apply with second coat.

### CLEANUP

Clean tools with A1 Solvent or Xylene.

### MAINTENANCE

Clean sealed surface with water only. Reseal surface every two years or as needed to prevent buildup of sealer.

**DISCLAIMER:** Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in USA

**CLEMONS CONCRETE COATINGS**

505 Cave Road Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052