

B-15, B-25, B-30

Water-Based Cure

DESCRIPTION

B Cures are a cross linking, styrene-acrylic copolymer solution formulated to achieve both a protective and decorative finish; as well as allow the concrete to attain full mix design properties. **B Cure** is a film-forming sealer, which will assist the curing of freshly placed concrete. **SUPER SEAL B** is formulated as follows:

- B-25 is a high 30% solids, water based, cure and seal that meets ASTM C309 A and B and ASTM C1315
- **B-25** is a medium 25% solids, water based, cure and seal that meets ASTM C309 A and B and ASTM C1315
- **B-15** is an economical, low viscosity, low 15% solids formula for easy spray ability that meets ASTM C309 A

FEATURES

★Satin Finish

★Low V.O.C.

★ Sprayable

★Non-yellowing

PREPARATION

Clean dirt, wax, grease, oil, and other contaminants from the surface. Be sure to remove any foreign coating unless the previous coating is the same or a similar water-based sealer. Make sure the surface has been cleaned and is dry. Clean oily concrete with Clemons DEGREASER NEUTRALIZER. Use a bristle brush for heavily oiled spots. If the surface is slick, etch with Clemons ETCH & CLEAN. Rinse well with Clemons DEGREASER NEUTRALIZER and a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause bubbles or streaking to form.

APPLICATION

Apply B Cure as soon as bleed water is gone and all finish work has been completed. Apply at a substrate temperature above 50° F. Apply with a sprayer. If applying to fresh concrete, wait until all the bleed water has evaporated. For exterior concrete, you may use a medium nap roller. For smooth concrete you may use a short nap roller and cross roll. Thoroughly saturate the surface. Apply additional coats as needed. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the dry.

NET COVERAGE RATE

Two thin coats are recommended.

Smooth Troweled: 300 ft² per gallon

Textured or Stamped: 200 ft² per gallon

Broom Swept: 200 ft² per gallon

TECHNICAL DATA

VOC: standard <180g/L

Flash Point: N/A

HMIS/NFPA

Health 1

Reactivity 0

Flammability 0

Protection B

Meets or Exceeds ASTM C-309, Type I Class A and B; ASTM C-1315 (WB-25 only); EPA 40 CFR Part D

CLEANUP

Clean tools with water.

DISCLAIMER: Since manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

Made in USA

CLEMONS CONCRETE COATINGS

505 Cave Road Nashville TN 37210 ★ www.ccc-usa.com ★ Tel: 615-872-9099 ★ Fax: 615-872-9052